

Adhesive film 13880 ® for markings

13880 adhemark-Ind:1

SUPPORT : PET base
COLOR : White
ADHESIVE : Permanent acrylic
LINER : blue pehd 80µ
THICKNESS : 75 µm
EXTERNAL LIFE TIME : 36 months

KEY POINTS :

- Permanent liveries
- Silk-Screen printing
- Very good external durability
- Excellent dimensional stability
- Ink system compatible Aviox clearcoat

TECHNICAL CHARACTERISTICS :

Description	Unit	Value	Test method
Peel adhesion :	N/cm	5,20	AFERA 4001 on steel mini value
breaking strength :	N/cm	67	AFERA 4004
Temperature stability :	°C	Min: -40 Max: +120	> 260°C on short term
Material is under homologation process for aircraft industrie			
Flexibility at room temperature d 10 mm ISO 1519 conforme no alteration			
Test quv uvb 313 - 1000h - (value without coating on) delta E repère lab black : 0 red : 1,5 green : 2,4 blue : 2,4 yellow : 0,5 white : 1,3			
Test arrachement ISO 4624 plot 20 mm 2,6 Mpa			

SHELF LIFE : 12 months