

SUPER PENETRATING, WATER DISPLACING CORROSION PREVENTIVE TEMPORARY PROTECTION

Approvals:

- **AIRBUS** **CML 15 -006A, IPS 09-08-001-03**
- **EADS CASA** **Z11504**
- **French Air Force (STPA)**
- **DASSAULT AVIATION**
- **EUROCOPTER** **IFM-EI-042 IF-MA 338**

Conforms to Specifications:

- **AIRBUS** **Type I Grade 3**
- **AIR 8062**
- **DASSAULT** **DGQT 1.7.0.103 Type I**

SOCOPAC 25H provides a thorough protection and water-repellent coat for materials, spare parts or assemblies, in the worst climatic conditions. The ultimate film forms a very efficient barrier against all the agents responsible for corrosion (water, oxygen, acids, basis and salts coming from industrial emissions, tropical atmospheres, etc...).

Its long lasting anti-corrosion power protects aluminium and alloys, steels, light alloys (titanium, magnesium), zinc and galvanized steel, copper and alloys and cadmium. It can be applied with no risk of attack to all painted surfaces, composite materials, plastics, rubbers, Plexiglas and polycarbonates (non crazing).

SOCOPAC 25H has been formulated to offer the highest safety for users as well as for the substrates to be protected; it does not contain any harmful solvents, toluene, xylene or chlorinated products.

- SOCOPAC 25H displaces water and humidity and, after drying, leaves a long term protective waterproof film which resists differences in temperature, heavy rain, sea air, tropical atmospheres or industrial corrosive atmospheres.

The film surface is dry and wax-like, which is especially interesting when the protection is to be applied on spare parts, which are frequently handled.

- However, thanks to its flexibility, the film absorbs slight impacts without damage or cracking.
- Because of its polarity and surfactant qualities, SOCOPAC 25H is bonded to the metal surface instead of the agents responsible for the corrosion.
- The cured film is formulated to resist outside for several years and above all to remain stable during this time. It is not subject to alteration by the air, or by exposure to sun or heat.

USES

Because of its exceptional properties in metal corrosion preventive protection, SOCOPAC 25H may be employed anywhere.

- In aerospace, it may be used when the risks of corrosion by condensation or by exposure to sea or corrosive air require an efficient and controllable temporary protection: landing gear, closed compartments, cabin and toilet floors, bunkers, pipe-work, cables, guide rails for containers, etc...

DIRECTIONS FOR USE

SOCOPAC 25H can be applied with a classic or airless gun or by dipping.

SOCOPAC 25H can be applied on humid surfaces. Its water-repelling feature allows it to displace humidity. However, in the case of hard to reach surfaces or particularly rough and wet surfaces, it is advised to use WADIS 24, a product with a greater water repelling and penetrative effect as a ground coat.

REMOVAL

Different methods can be used to strip the SOCOPAC 25H film depending on the equipment available and local conditions:

- 1) With cleaning solvents without rinsing with water, use **HYSO 96** or **98** or **DIESTONE DLS** for accelerated drying.
- 2) With aqueous cleaners followed by rinsing with water, use **HYSOMUL MC**. After 10 minutes, rinse with a jet of water, preferably hot.
- 3) In a steam cleaning machine, increase the temperature over 80°C (176°F); some HYSOMUL MC (10 to 20 %) may be added. It is also possible to add a **SYNCLAIR (A/C)**.



TECHNICAL CHARACTERISTICS

• Appearance	thixotropic liquid
• Density at 20°C (68°F)	0.87
• Flash point (ISO 2592)	40°C (104°F)
• Viscosity (ISO 2431 - n° 3)	37 seconds
• Covering power for 10 microns "dry"	37 m ² /l
• Colour	brown - red
• Recommended dry film thickness	10 to 25 microns
• Drying time (film of 10 µ "dry" at 20°C / 68°F):	
- fast to handling	1 to 2 hours
- total drying	5 to 6 hours

PROTECTIVE FILM PERFORMANCES

• Film appearance	dry wax-like
• Thickness if sprayed	10 to 25 microns
• Thickness if dipped	10 to 20 microns
• Resistance to temperature	-55 to +120° C (-67 to +248° F)
• Resistance to humid tropical air on steel (chamber at 95°F and 100 % humidity)	> 6 months (dry film of 25 µ)
• Resistance to alternated immersion into sea water on steel (AIR 0761/NFA 91411).....	> 500 hours (25 µ)
• Resistance to salt spray ASTM B117-94 on steel (XC18S) ; depending on thickness	10 µ = > 100 hours 25 µ = > 400 hours 50 µ = > 750 hours
• Resistance to salt spray ASTM B117-94 on alloyed aluminium (2024)	> 500 hours (25 µ)



Support technique International / International Technical Support
tel. +33 (0)2 97 43 76 90 fax +33 (0)2 97 54 50 26 E-mail Support@socomore.com

Pour connaître notre correspondant le plus proche / To find our nearest correspondent
socomore@socomore.com

PRECAUTIONS FOR USE AND STORAGE

SOCOPAC 25H is free from harmful, chlorinated or aromatic hydrocarbons, and is not flammable in normal conditions of use.

However, as for all hydrocarbon based products, it is recommended to take the normal precautions for use and store away from flames and heat sources. Wear gloves during application and eye protection.

Store in the original closed packages, away from heat sources and flames. Always shake well before use.

Please consult the safety data sheet for further information.

This technical data sheet replaces and cancels the previous one.

The above details have been compiled to the best of our knowledge, they have, however, an indicative value only, and we therefore make no warranties and assume no liability in connection with any use of this information, particularly if a third party's rights are affected by the use of our products. The above information has been compiled based upon tests carried out by SOCOMORE ; all data is subject to change as SOCOMORE deems appropriate. The data given is not intended to substitute for any testing you must conduct in order to determine the suitability of the product for your particular purposes. Please check your local legislation applicable to the use of this product. Should you need any further information please contact our services.



Support technique International / International Technical Support
tel. +33 (0)2 97 43 76 90 fax +33 (0)2 97 54 50 26 E-mail Support@socomore.com

Pour connaître notre correspondant le plus proche / To find our nearest correspondent
socomore@socomore.com

Socopac 25H_19193AGGB

date : 6 May 2009

Written and checked by: BLT

socomore
finishing solutions

Approved by: JPF

4/4